

FICHA TÉCNICA

YESO DURO ROSA TIPO IV/4		
REFERENCIAS	25661	
FABRICANTE / RESPONSABLE	MADESPA, S.A. C/ Río Jarama, 120, 45007, Toledo España	
CLASIFICACIÓN	Producto No Sanitario (Clase protésico).	
DESCRIPCIÓN	Baja expansión y elevada dureza superficial. Tixotrópico. Su óptima fluidez bajo vibración permite reproducir con fidelidad todos los detalles de la impresión. Compatible con todos los materiales de impresión. Conforme norma I.S.O. 6873	
ESPECIFICACIÓN	- Proporción de mezcla agua/polvo: 22-23 ml/100 gr. - Tiempo de trabajo: 6'-7'. - Expansión de fraguado (2h): ~0,09 %. - Resistencia a la compresión (1h): ~35 MPa.	
COMPOSICIÓN	Sulfato de calcio.	
PRESENTACIÓN	1 unidad de 25 kg.	
VIDA ÚTIL	3 años.	
INSTRUCCIONES DE USO	Poner agua en una taza y añadir lentamente el polvo según la proporción recomendada. Se recomienda utilizar vibrador.	
FINALIDAD PREVISTA	Yeso duro tipo IV, de color rosa, indicado tanto para trabajos en clínica como en laboratorio, para la realización de modelos en prótesis fija, esqueléticos y prótesis removible.	
ALMACENAMIENTO Y TRANSPORTE	Conservar los envases en un lugar seco, bien ventilado y protegido de la humedad.	

TECHNICAL DATA SHEET

TYPE IV GYPSUM PINK		
REFERENCES	25661	
MANUFACTURER	MADESPA, S.A. C/ Río Jarama, 120, 45007, Toledo Spain	
CLASSIFICATION	Non-Sanitary Product (Prosthetic Class).	
DESCRIPTION	Low expansion and high surface hardness. Thixotropic. Its optimum fluidity under vibration allows to reproduce with fidelity all the details of the printing. Compatible with all printing materials. Conforms to I.S.O. 6873 standard.	
SPECIFICATION	- Mixing ratio water/powder: 22-23 ml/100 gr. - Working time: 6'-7'. - Setting expansion (2h): ~0.09 %. - Compressive strength (1h): ~35 MPa.	
COMPOSITION	Calcium sulfate.	
PACKAGE	1 unit of 25 kg.	
SHELF LIFE	3 years.	
INSTRUCTIONS FOR USE	Put water in a cup and slowly add the powder according to the recommended proportion. The use of a vibrator is recommended.	
INTENDED USE	Type IV hard plaster, pink color, suitable for both clinical and laboratory work, for the realization of models in fixed prosthesis, skeletal and removable prosthesis.	
STORAGE AND TRANSPORT	Store containers in a dry, well-ventilated place, protected from humidity.	