

FICHA TÉCNICA

YESO DURO TIPO IV/4 MARFIL		
REFERENCIAS	H62018	
FABRICANTE / RESPONSABLE	MADESPA, S.A. C/ Río Jarama, 120, 45007, Toledo España	
CLASIFICACIÓN	Producto No Sanitario (Clase protésico).	
DESCRIPCIÓN	Extraduro, de optima fluidez durante la preparación del modelo. Yeso Tixotrópico que tiene una gran fluidez bajo leve vibración. Compatible con todos los materiales de impresión. Conforme norma I.S.O. 6873.	
ESPECIFICACIÓN	Color Marfil. Tipo 4. Proporción de mezcla: 22/23ml-100gr Tiempo de trabajo: 6'-7' Fraguado final: 10'-13' Expansión de fraguado: 0,09% Resistencia a la compresión (1h): 39 MPa Tiempo de mezcla bajo vacío: 30'' Tiempo de mezcla manual: 60''	
COMPOSICIÓN	Sulfato de calcio.	
PRESENTACIÓN	1 unidad de 25 kg.	
VIDA ÚTIL	3 años.	
INSTRUCCIONES DE USO	Poner agua en una taza y añadir lentamente el polvo según la proporción recomendada. Se recomienda utilizar vibrador.	
FINALIDAD PREVISTA	Utilizado para muñones desmontables para coronas y puentes y prótesis removibles totales o parciales realizadas ya sea en muflas convencionales o por inyección. Se recomienda también para modelos esqueléticos	
ALMACENAMIENTO Y TRANSPORTE	Conservar los envases en un lugar seco, bien ventilado y protegido de la humedad.	

TECHNICAL DATA SHEET

EXTRA HARD GYPSUM TYPE IV/4 IVORY		
REFERENCES	H62018	
MANUFACTURER	MADESPA, S.A. C/ Río Jarama, 120, 45007, Toledo Spain	
CLASSIFICATION	Non-Sanitary Product (Prosthetic Class).	
DESCRIPTION	Extra hard, with optimum fluidity during the preparation of the model. Thixotropic plaster that has a great fluidity under slight vibration. Compatible with all impression materials. Conforms to I.S.O. 6873 standard.	
SPECIFICATION	Ivory color. Type 4. Mixing ratio: 22/23ml-100gr. Working time: 6'-7'. Final setting: 10'-13'. Setting expansion: 0,09%. Compressive strength (1h): 39 MPa Mixing time under vacuum: 30 Manual mixing time: 60".	
COMPOSITION	Calcium sulfate.	
PACKAGE	1 unit of 25 kg.	
SHELF LIFE	3 years.	
INSTRUCTIONS FOR USE	Put water in a cup and slowly add the powder according to the recommended proportion. The use of a vibrator is recommended.	
INTENDED USE	Used for removable dies for crowns and bridges and total or partial removable prostheses made either in conventional muffles or by injection. It is also recommended for skeletal models	
STORAGE AND TRANSPORT	Store containers in a dry, well-ventilated place, protected from humidity.	