

# anax DENT

adhesion & bonding

Over PMMA, acrylic & BisGma / sobre PMMA, acrílico & BisGma

1. Mechanical retention over framework



2. Cleaning / steamer



3. Sandblast 50 microns / 1,5 bars. Acrylic Cleaning / steamer



4. Bond LC ( light curing ), 1,5 min.



5. Composite  
Acrylic  
Other brand



Composite, ceramics & and natural tooth