FICHA TÉCNICA

YESO NATURAL DURO TIPO III/3		
REFERENCIAS	H62011: Yeso duro tipo III amarillo 25kg caja Proc. H62012: Yeso duro tipo III Azul 25 kg caja Proc. H62013: Yeso duro tipo III Rosa 25 kg caja Proc.	
FABRICANTE / RESPONSABLE	**MADESPA, S.A.** C/ Río Jarama, 120, 45007, Toledo España	
CLASIFICACIÓN	Producto No Sanitario (Clase protésico).	
DESCRIPCIÓN	Dotado de una fluidez óptima, su consistencia garantiza la fiel reproducción de los detalles de la impresión. Es compatible con todos los materiales de impresión. Conforme norma I.S.O. 6873.	
ESPECIFICACIÓN	Proporción de mezcla: 26ml-100gr Tiempo de trabajo: 4’ 30’’-6’ Fraguado final: 8’-14’ Expansión de fraguado: 0,10% Resistencia a la compresión (1h): 33 MPa Tiempo de mezcla bajo vacío: 30’’ Tiempo de mezcla manual: 60’’	
COMPOSICIÓN	Sulfato de calcio.	
PRESENTACIÓN	1 unidad de 25 kg.	
VIDA ÚTIL	3 años.	
INSTRUCCIONES DE USO	Poner agua en una taza y añadir lentamente el polvo según la proporción recomendada. Se recomienda utilizar vibrador.	
FINALIDAD PREVISTA	Prótesis removibles totales o parciales. Modelos antagonistas	
ALMACENAMIENTO Y TRANSPORTE	Conservar los envases en un lugar seco, bien ventilado y protegido de la humedad.	

TECHNICAL DATA SHEET

HARD NATURAL GYPSUM TYPE III/3		
REFERENCES	H62011: Hard natural gypsum type III yellow 25kg caja Proc. H62012: Hard natural gypsum type III blue 25 kg caja Proc. H62013: Hard natural gypsum type III Pink 25 kg caja Proc.	
MANUFACTURER	**MADESPA, S.A.** C/ Río Jarama, 120, 45007, Toledo Spain	
CLASSIFICATION	Non-Sanitary Product (Prosthetic Class).	
DESCRIPTION	Endowed with optimum fluidity, its consistency guarantees the faithful reproduction of print details. It is compatible with all printing materials. Conforms to I.S.O. 6873 standard.	
SPECIFICATION	Mixing ratio: 26ml-100gr Working time: 4' 30''-6''. Final setting: 8'-14'. Setting expansion: 0,10%. Compressive strength (1h): 33 MPa Mixing time under vacuum: 30 Manual mixing time: 60''.	
COMPOSITION	Calcium sulfate.	
PACKAGE	1 unit of 25 kg.	
SHELF LIFE	3 years.	
INSTRUCTIONS FOR USE	Put water in a cup and slowly add the powder according to the recommended proportion. The use of a vibrator is recommended.	
INTENDED USE	Total or partial removable prosthesis. Antagonist models	
STORAGE AND TRANSPORT	Store containers in a dry, well-ventilated place, protected from humidity.	